



TECHNICAL DATA SHEET

FIRESOUND™

Description

FiresoundTM is a one part, water based construction sealant for sealing joints and penetrations where fire resistance is required, or where an acoustic rated sealant is required.

Benefits

- Fire rating for gaps up to 50mm
- Intumescent, expands when exposed to fire or heat above 90°C
- +/- 20% joint movement capability
- Non flammable
- Water clean up
- Non toxic, contains no heavy metals such as antimony, cadmium, lead or mercury
- Isocyante free
- Asbestos free
- **Excellent Acoustic properties**
- Excellent UV stability and weather resistance
- Australian Made
- Very easy to apply and gives a smooth finish
- Low odour
- Paintable
- Priming not normally required
- Can be applied to damp surfaces

Uses

- Sealing exterior and interior construction joints that are subject to movement (up to ±20%) in pre-cast concrete panels. blockwork and brickwork
- Gaps around cables, metal pipes, conduits, busways and ducts that penetrate walls, floors and ceilings

If joint movement is not required, Firesound can be used as a putty for filling holes in fire rated substrates

Compatible Substrates

Concrete	Cable coverings (PVC)		
Mortar	Plasterboard		
Steel	Aluminium		

Coverage per liter

Joint dimensions (mm)						
	10	20	30	40	50	
	mm mm mm m					
10mm	10m	5m	-	-	-	
15mm	-	-	2m	1.6m	-	
20mm	-	-	-	1.3m	1.0m	
25mm	-	-	-	-	0.5m	

Standards Compliance

Firesound™ sealant has a four (4) hour fire rating when tested in accordance with AS1530.4 - 1990 supplemented by AS4072.1 - 1992 as well as BS476: part 20; 1987 and as appropriate on a gap-sealing system protecting joints between concrete panels. Due to variations in fire rating results using different thicknesses and types of substrates. advice should be sought concerning the suitability of FiresoundTM in specific applications.

Firesound™ has been tested in accordance with AS1276.1 and found to perform as an excellent acoustic sealant with Sound Transmission Class (STC) 65 rating in a wall constructed using 2 leaves of aerated concrete plus plasterboard facings. In tests involving 10mm joints in brick walls, Sound Insulation Rating of Rw + Ctr 49 was achieved in a 220mm brick wall, and Rw + Ctr 55 in a 220mm brick wall with plasterboard facing. As

Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

NOTE TO USER: by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.







技术资料

TECHNICAL DATA SHEET

acoustic performance is determined according to the type and dimension of substrates, advice should be sought regarding the overall design concept.

Firesound™ meets the requirements of LEED Certification: Indoor Environmental Quality - Credit 4.1 (Low-Emitting Materials: Adhesives and Sealants). See MSDS for VOC value. In many regions applicators of fire rated sealants require certification or licences - check local regulations to ensure compliance.

	Schedule of Acoustic Test Configurations and Results Summary AS1276.1							
Te st	Wall	Gap	Coverin g	Ga p	ST C	Rw	Ct r	Rw + Ctr
2	110 brick wall	Firesound	Standar d Brick	45	45	-4	41	2
5	220 brick wall	Firesound	Standar d Brick	54	54	-5	49	5
14	220 brick wall	blocked	Standar d Brick & Plasterb oard	71	66	-11	55	14

Performance Summary

Colour	Grey and white
Skinning time	15 minutes
Working time	30 minutes
Hardness (Shore D)	25-35
Service temperature	-20°C to 80°C
Specific Gravity	~1.5

Surface Preparation

Ensure substrate surfaces are clean, sound, dry and free of oil, grease and surface contaminants such as dust, loose particles, release agents, silicone and water repellents.

Ideally surfaces should be dry. FiresoundTM sealant will adhere to slightly damp surfaces, but avoid wet surfaces. Areas adjacent to joints may be masked to provide a neat finish. Masking should be removed immediately after tooling. Ensure FiresoundTM is applied to sealed edges of plasterboard. Unsealed edges (with no primer) may lead to a weak bond being formed and / or loss of acoustic performance.

Priming

Should priming be needed to seal edges or increase adhesion then Fullers Express 290D primer should be used. A coat should be brushed on and left to dry before FiresoundTM is applied. Priming is recommended for porous or difficult to clean surfaces.

Application

Apply Firesound™ in ambient conditions between 5 and 35 degrees centigrade. Higher temperatures should be avoided to prevent the possibility bubbling of the sealant due to rapid moisture evaporation. Do not apply below 5 degrees centigrade. Fill joint with trowel or caulking gun, then tool off with a spatula and clean off excess with a damp cloth. Protect from water for at least 24 hours until a suitable skin has cured (will require significantly longer at temperatures below 15 degrees centigrade). Some shrinkage is normal during curing, and should be anticipated when measuring joints.

Curing

Time to cure is highly variable and depends on weather conditions, ambient temperature and depth of joint. Allow longer curing times in cold or damp conditions. Do not allow water contact until at least a thick surface has formed.

Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

NOTE TO USER: by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

Australia
Tel: +61 1800 423 855
customer.service@hbfuller.com
China & Hong Kong
Tel: +86 20 82068291
cs.china@hbfuller.com
Indonesia

Tel: +62-21-5307232/33

Tel: +82 2 786 8296
com cskorea@hbfuller.com
Malaysia
Tel: +603 3345 5200
New Zealand
Tel: +64 800 555 072
customer.service@hbfuller.com

Korea

Philippines
Tel: +63 2 5194073
Taiwan
Tel: +886 2 26033385
Thailand
Tel: +66 2 3757442
Vietnam

Tel: +84 8 22225588







技术资料

TECHNICAL DATA SHEET

Clean Up

After applying Firesound™, clean all tools and metal surfaces with warm water while the sealant is still wet. Cured sealant will need to be removed mechanically.

Painting

Firesound™ sealant is suitable for painting when cured. To minimize paint cracking, at least 24 hours should be left before painting where possible. In standard conditions (25 degrees centigrade) Firesound™ may be painted after 6 hours, however, care should be taken to ensure a flexible acrylic coating is used and that a firm skin has developed. In cooler conditions or where the humidity is high, allow a longer cure period before painting.

Limitations

- Do not apply to wet surfaces.
- Firesound™ sealant may be used both for interior and exterior sealing, but not suitable for use in water retaining structures or where pooling of water may
- Firesound[™] sealant has good servicing characteristics when unprotected in internal applications.
- For external use, Firesound™ sealant must be protected from rain or water, until such time as the sealant builds up a thick skin to avoid washout. Therefore do not apply sealant when rain exposure is likely, or before a thick skin can develop. This is typically 24 hours in summer (25 to 30 degrees C), but will be significantly longer in winter, or at times of high humidity
- In many regions applicators of fire rated sealants require certification or licenses check local regulations to ensure compliance

Safety Information

Firesound™ is not classified as hazardous according to criteria of Worksafe Australia. A Material Safety Data Sheet is available from the H.B. Fuller representative your state, HB Fuller Australia customer service, or downloadable from the HB Fuller web site, www.hbfuller.com.au

Disclaimer

This technical data sheet summarises at the date of issue to the best technical knowledge of HB Fuller Australia. Since HB Fuller Australia cannot anticipate or control the conditions under which the product may be used, each user must, prior to usage, review this technical data sheet in the context of how the user intends to handle and use the product in the workplace. If clarification or further information is needed to ensure that an appropriate assessment can be made, the user should contact this company. Our responsibility for the products sold is subject to our standard terms and conditions, a copy of which is sent to our customers and is also available on request

> Version 3 TDS Date: 23/12/2013

Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a quarantee of performance.

NOTE TO USER: by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

Tel: +62-21-5307232/33

Korea

